

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
28 April 2005 (28.04.2005)

PCT

(10) International Publication Number  
**WO 2005/037744 A1**

(51) International Patent Classification<sup>7</sup>: **C07C 19/08**,  
17/20, 17/21, 17/23

(21) International Application Number:  
PCT/US2004/034455

(22) International Filing Date: 13 October 2004 (13.10.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/511,354 14 October 2003 (14.10.2003) US

(71) Applicant (for all designated States except US): **E.I. DUPONT DE NEMOURS AND COMPANY** [US/US];  
1007 Market Street, Wilmington, DE 19898 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **RAO, Velliyur, Nott, Mallikarjuna** [US/US]; 1 Georgetown Avenue, Wilmington, DE 19809 (US). **SIEVERT, Allen, Capron** [US/US];  
215 Rhett Lane, Elkton, MD 21921 (US).

(74) Agent: **HEISER, David, E.**; E. I. Du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: PROCESS FOR THE PREPARATION OF 1,1,1,3,3-PENTAFLUOROPROPANE AND 1,1,1,3,3,3-HEXAFLUOROPROPANE

(57) Abstract: A process for the manufacture of  $\text{CF}_3\text{CH}_2\text{CHF}_2$  and  $\text{CF}_3\text{CH}_2\text{CF}_3$  is disclosed. The process involves (a) reacting HF and at least one halopropene of the formula  $\text{CX}_3\text{CCl}=\text{CClX}$  (where each X is independently F or Cl) to produce a product including both  $\text{CF}_3\text{CCl}=\text{CF}_2$  and  $\text{CF}_3\text{CHClCF}_3$ ; (b) reacting  $\text{CF}_3\text{CCl}=\text{CF}_2$  and  $\text{CF}_3\text{CHClCF}_3$  produced in (a) with hydrogen to produce a product including both  $\text{CF}_3\text{CH}_2\text{CHF}_2$  and  $\text{CF}_3\text{CH}_2\text{CF}_3$ ; and (c) recovering  $\text{CF}_3\text{CH}_2\text{CHF}_2$  and  $\text{CF}_3\text{CH}_2\text{CF}_3$  from the product produced in (b). In (a), the  $\text{CF}_3\text{CCl}=\text{CF}_2$  and  $\text{CF}_3\text{CHClCF}_3$  are produced in the presence of a fluorination catalyst including a  $\text{ZnCr}_2\text{O}_4$ /crystalline  $\alpha$ -chromium oxide composition, a  $\text{ZnCr}_2\text{O}_4$ /crystalline  $\alpha$ -chromium oxide composition which has been treated with a fluorinating agent, a zinc halide/ $\alpha$ -chromium oxide composition and/or a zinc halide/ $\alpha$ -chromium oxide composition which has been treated with a fluorinating agent.

# TITLE

## PROCESS FOR THE PREPARATION OF 1,1,1,3,3-PENTAFLUOROPROPANE AND 1,1,1,3,3,3-HEXAFLUOROPROPANE

### FIELD OF THE INVENTION

5 This invention relates to the synthesis of 1,1,1,3,3-pentafluoropropane and 1,1,1,3,3,3-hexafluoropropane.

### BACKGROUND

A number of chlorine-containing halocarbons are considered to be detrimental toward the Earth's ozone layer. There is a world-wide effort to  
10 develop materials having lower ozone depletion potential that can serve as effective replacements. For example, the hydrofluorocarbon, 1,1,1,2-tetrafluoroethane (HFC-134a) is being used as a replacement for dichlorodifluoromethane (CFC-12) in refrigeration systems. There is a need for manufacturing processes that provide halogenated hydrocarbons  
15 that contain less chlorine or no chlorine. The production of hydrofluorocarbons (i.e., compounds containing only carbon, hydrogen and fluorine), has been the subject of considerable interest to provide environmentally desirable products for use as solvents, blowing agents, refrigerants, cleaning agents, aerosol propellants, heat transfer media,  
20 dielectrics, fire extinguishants and power cycle working fluids. For example, 1,1,1,3,3-pentafluoropropane has utility as a blowing agent, and 1,1,1,3,3,3-hexafluoropropane has utility as a fire extinguishant and as a refrigerant.

### SUMMARY OF THE INVENTION

25 This invention provides a process for the manufacture of 1,1,1,3,3-pentafluoropropane (HFC-245fa) and 1,1,1,3,3,3-hexafluoropropane (HFC-236fa). The process comprises (a) reacting HF and at least one halopropene of the formula  $CX_3CCl=CClX$ , wherein each X is independently selected from the group consisting of F and Cl, to produce a  
30 product comprising  $CF_3CCl=CF_2$  and  $CF_3CHClCF_3$ , wherein said  $CF_3CCl=CF_2$  and  $CF_3CHClCF_3$  are produced in the presence of a fluorination catalyst comprising at least one composition selected from the group consisting of (i) compositions comprising  $ZnCr_2O_4$  and crystalline  $\alpha$ -chromium oxide, (ii) compositions comprising a zinc halide and  $\alpha$ -chromium oxide and (iii) compositions of (i) or (ii) which have been treated  
35 with a fluorinating agent (e.g., anhydrous hydrogen fluoride); (b) reacting  $CF_3CCl=CF_2$  and  $CF_3CHClCF_3$  produced in (a) with hydrogen ( $H_2$ ), optionally in the presence of HF, to produce a product comprising

CF<sub>3</sub>CH<sub>2</sub>CHF<sub>2</sub> and CF<sub>3</sub>CH<sub>2</sub>CF<sub>3</sub>; and (c) recovering CF<sub>3</sub>CH<sub>2</sub>CHF<sub>2</sub> and CF<sub>3</sub>CH<sub>2</sub>CF<sub>3</sub> from the product produced in (b).

#### DETAILED DESCRIPTION

This invention provides a process for the preparation of  
5 CF<sub>3</sub>CH<sub>2</sub>CHF<sub>2</sub> (HFC-245fa) and CF<sub>3</sub>CH<sub>2</sub>CF<sub>3</sub> (HFC-236fa). The HFC-245fa and HFC-236fa may be recovered as individual products and/or as one or more mixtures of the two products.

In step (a) of the process of this invention, one or more halopropene compounds CX<sub>3</sub>CCl=CClX, wherein each X is independently selected  
10 from the group consisting of F and Cl, are reacted with hydrogen fluoride (HF) to produce a product mixture comprising CF<sub>3</sub>CCl=CF<sub>2</sub> (CFC-1215xc) and CF<sub>3</sub>CHClCF<sub>3</sub> (HCFC-226da). Accordingly, this invention provides a process for the preparation of mixtures of CF<sub>3</sub>CCl=CF<sub>2</sub> (CFC-1215xc) and CF<sub>3</sub>CHClCF<sub>3</sub> (HCFC-226da) from readily available starting materials.

15 Suitable starting materials for the process of this invention include E- and Z-CF<sub>3</sub>CCl=CClF (CFC-1214xb), CF<sub>3</sub>CCl=CCl<sub>2</sub> (CFC-1213xa), CCIF<sub>2</sub>CCl=CCl<sub>2</sub> (CFC-1212xa), CCl<sub>2</sub>FCCl=CCl<sub>2</sub> (CFC-1211xa), and CCl<sub>3</sub>CCl=CCl<sub>2</sub> (hexachloropropene, HCP), or mixtures thereof.

Due to their availability, CF<sub>3</sub>CCl=CCl<sub>2</sub> (CFC-1213xa) and  
20 CCl<sub>3</sub>CCl=CCl<sub>2</sub> (hexachloropropene, HCP) are the preferred starting materials for the process of the invention.

Preferably, the reaction of HF with CX<sub>3</sub>CCl=CClX is carried out in the vapor phase in a heated tubular reactor. A number of reactor configurations are possible, including vertical and horizontal orientation of  
25 the reactor and different modes of contacting the halopropene starting material(s) with HF. Preferably the HF is substantially anhydrous.

In one embodiment of step (a), the halopropene starting material(s) may be fed to the reactor containing the fluorination catalyst. The halopropene starting material(s) may be initially vaporized and fed to the  
30 reactor as gas(es).

In another embodiment of step (a), the halopropene starting material(s) may be contacted with HF in a pre-reactor. The pre-reactor may be empty (i.e., unpacked), but is preferably filled with a suitable packing such as Monel™ or Hastelloy™ nickel alloy turnings or wool, or  
35 other material inert to HCl and HF which allows efficient mixing of CX<sub>3</sub>CCl=CClX and HF.

If the halopropene starting material(s) are fed to the pre-reactor as liquid(s), it is preferable for the pre-reactor to be oriented vertically with

$CX_3CCl=CClX$  entering the top of the reactor and pre-heated HF vapor introduced at the bottom of the reactor.

Suitable temperatures for the pre-reactor are within the range of from about 80°C to about 250°C, preferably from about 100°C to about 200°C. Under these conditions, for example, hexachloropropene is converted to a mixture containing predominantly CFC-1213xa. The starting material feed rate is determined by the length and diameter of the reactor, the temperature, and the degree of fluorination desired within the pre-reactor. Slower feed rates at a given temperature will increase contact time and tend to increase the amount of conversion of the starting material and increase the degree of fluorination of the products.

The term "degree of fluorination" means the extent to which fluorine atoms replace chlorine substituents in the  $CX_3CCl=CClX$  starting materials. For example,  $CF_3CCl=CClF$  represents a higher degree of fluorination than  $CClF_2CCl=CCl_2$  and  $CF_3CHClCF_3$  represents a higher degree of fluorination than  $CClF_2CHClCF_3$ .

The molar ratio of HF fed to the pre-reactor, or otherwise to the reaction zone of step (a), to halopropene starting material fed in step (a), is typically from about stoichiometric to about 50:1. The stoichiometric ratio depends on the average degree of fluorination of the halopropene starting material(s) fed to the pre-reactor and is typically based on formation of  $C_3ClF_5$ . For example, if the halopropene is HCP, the stoichiometric ratio of HF to HCP is 5:1; if the halopropene is CFC-1213xa, the stoichiometric ratio of HF to CFC-1213xa is 2:1. Preferably, the molar ratio of HF to halopropene starting material is from about twice the stoichiometric ratio (based on formation of  $C_3ClF_5$ ) to about 30:1. Higher ratios than 30:1 are not particularly beneficial. Lower ratios of HF to halopropene result in reduced yields of CFC-1215xc and HCFC-226da. Typically, for a given catalyst, higher HF feed ratios will tend to favor formation of HCFC-226da relative to CFC-1215xc.

In a preferred embodiment of this invention, in step (a) of the process, the halopropene starting materials are vaporized, preferably in the presence of HF, contacted with HF in a pre-reactor, and then contacted with the fluorination catalyst. If the preferred amount of HF is fed in the pre-reactor, additional HF is not required when the effluent from the pre-reactor contacts the fluorination catalyst.

Suitable temperatures for catalytic fluorination of halopropene starting materials and/or their products formed in the pre-reactor are within

the range of about 200°C to about 400°C, preferably from about 240°C to about 350°C. Higher temperatures typically contribute to reduced catalyst life. Temperatures below about 240°C may result in substantial amounts of products having a degree of fluorination less than five (i.e.,

5 underfluorinates). Suitable reactor pressures for vapor phase embodiments of this invention may be in the range of from about 1 to about 30 atmospheres. Reactor pressures of about 5 atmospheres to about 20 atmospheres may be advantageously employed to facilitate separation of HCl from other reaction products in step (b) of the process.

10 The fluorination catalysts which are used in the process of the present invention are preferably compositions comprising  $\text{ZnCr}_2\text{O}_4$  (zinc chromite) and crystalline  $\alpha\text{-Cr}_2\text{O}_3$  ( $\alpha$ -chromium oxide) or compositions obtained by treatment of said compositions comprising  $\text{ZnCr}_2\text{O}_4$  (zinc chromite) and crystalline  $\alpha\text{-Cr}_2\text{O}_3$  ( $\alpha$ -chromium oxide) with a fluorinating agent. The amount of zinc relative to the total of chromium and zinc in these compositions is preferably from about 1 atom % to about 25 atom %.

Of note are chromium-containing catalyst compositions comprising  $\text{ZnCr}_2\text{O}_4$  (zinc chromite) and crystalline  $\alpha$ -chromium oxide wherein the  $\text{ZnCr}_2\text{O}_4$  contains between about 10 atom percent and 67 atom percent of the chromium in the composition and at least about 70 atom percent of the zinc in the composition, and wherein at least about 90 atom percent of the chromium present as chromium oxide in the composition is present as  $\text{ZnCr}_2\text{O}_4$  or crystalline  $\alpha$ -chromium oxide. Also of note are chromium-containing catalyst compositions, prepared by treatment of such

20 compositions comprising  $\text{ZnCr}_2\text{O}_4$  and crystalline  $\alpha$ -chromium oxide with a fluorinating agent. Also of note are such chromium-containing catalyst compositions which comprise  $\text{ZnCr}_2\text{O}_4$  and crystalline  $\alpha$ -chromium oxide wherein the  $\text{ZnCr}_2\text{O}_4$  contains between about 20 atom percent and about 50 atom percent of the chromium in the composition. Also of note are

25 such chromium-containing catalyst compositions which comprise  $\text{ZnCr}_2\text{O}_4$  and crystalline  $\alpha$ -chromium oxide wherein the  $\text{ZnCr}_2\text{O}_4$  contains at least about 90 atom percent of the zinc in the composition. Also of note are such chromium-containing catalyst compositions comprising zinc chromite and crystalline  $\alpha$ -chromium oxide wherein greater than 95 atom percent of

30 the chromium that is not present as zinc chromite is present as crystalline  $\alpha$ -chromium oxide. Also of note are such chromium-containing catalyst compositions which consist essentially of  $\text{ZnCr}_2\text{O}_4$  (zinc chromite) and crystalline  $\alpha$ -chromium oxide.

35

These compositions may be prepared, for example, by co-precipitation methods followed by calcination.

In a typical co-precipitation procedure, an aqueous solution of zinc and chromium(III) salts is prepared. The relative concentrations of the zinc and chromium(III) salts in the aqueous solution is dictated by the bulk atom percent zinc relative to chromium desired in the final catalyst. Therefore, the concentration of zinc in the aqueous solution is from about 1 mole % to about 25 mole % of the total concentration of zinc and chromium in the solution. The concentration of chromium(III) in the aqueous solution is typically in the range of 0.3 to 3 moles per liter with 0.75-1.5 moles per liter being a preferred concentration. While different chromium (III) salts might be employed, chromium(III) nitrate or its hydrated forms such as  $[\text{Cr}(\text{NO}_3)_3(\text{H}_2\text{O})_9]$ , are the most preferred chromium(III) salts for preparation of said aqueous solution.

While different zinc salts might be employed for preparation of said aqueous solutions, preferred zinc salts for preparation of catalysts for the process of this invention include zinc(II) nitrate and its hydrated forms such as  $[\text{Zn}(\text{NO}_3)_2(\text{H}_2\text{O})_6]$ .

The aqueous solution of the chromium(III) and zinc salts may then be evaporated either under vacuum or at elevated temperature to give a solid which is then calcined.

It is preferred to treat the aqueous solution of the chromium(III) and zinc salts with a base such as ammonium hydroxide (aqueous ammonia) to precipitate the zinc and chromium as the hydroxides. Bases containing alkali metals such as sodium or potassium hydroxide or the carbonates may be used but are not preferred. The addition of ammonium hydroxide to the aqueous solution of the chromium(III) and zinc salts is typically carried out gradually over a period of 1 to 12 hours. The pH of the solution is monitored during the addition of base. The final pH is typically in the range of 6.0 to 11.0, preferably from about 7.5 to about 9.0, most preferably about 8.0 to about 8.7. The precipitation of the zinc and chromium hydroxide mixture is typically carried out at a temperature of about 15°C to about 60°C, preferably from about 20°C to about 40°C. After the ammonium hydroxide is added, the mixture is typically stirred for up to 24 hours. The precipitated chromium and zinc hydroxides serve as precursors to  $\text{ZnCr}_2\text{O}_4$  and  $\alpha$ -chromium oxide.

After the precipitation of the zinc and chromium hydroxide mixture is complete, the mixture is dried. This may be carried out by evaporation in

an open pan on a hot plate or steam bath or in an oven or furnace at a suitable temperature. Suitable temperatures include temperatures from about 60°C to about 130°C (for example, about 100°C to about 120°C). Alternatively, the drying step may be carried out under vacuum using, for example, a rotary evaporator.

Optionally, the precipitated zinc and chromium hydroxide mixture may be collected and, if desired, washed with deionized water before drying. Preferably the precipitated zinc and chromium hydroxide mixture is not washed prior to the drying step.

After the zinc and chromium hydroxide mixture has been dried, the nitrate salts are then decomposed by heating the solid from about 250°C to about 350°C. The resulting solid is then calcined at temperatures of from about 400°C to about 1000°C, preferably from about 400°C to about 900°C.

Further information on the zinc and chromium compositions useful for this invention is provided in U. S. Patent Application 60/511,353 [CL2244 US PRV] filed October 14, 2003, and hereby incorporated by reference herein in its entirety (see also corresponding International Application No. PCT/US2004/\_\_\_\_\_).

The calcined zinc chromite/ $\alpha$ -chromium oxide compositions of the present invention may be pressed into various shapes such as pellets for use in packing reactors. It may also be used in powder form.

Typically, the calcined compositions will be pre-treated with a fluorinating agent prior to use as catalysts for changing the fluorine content of halogenated carbon compounds. Typically this fluorinating agent is HF though other materials may be used such as sulfur tetrafluoride, carbonyl fluoride, and fluorinated carbon compounds such as trichlorofluoromethane, dichlorodifluoromethane, chlorodifluoromethane, trifluoromethane, or 1,1,2-trichlorotrifluoroethane. This pretreatment can be accomplished, for example, by placing the catalyst in a suitable container which can be the reactor to be used to perform the process in the instant invention, and thereafter, passing HF over the dried, calcined catalyst so as to partially saturate the catalyst with HF. This is conveniently carried out by passing HF over the catalyst for a period of time, for example, about 0.1 to about 10 hours at a temperature of, for example, about 200°C to about 450°C. Nevertheless, this pretreatment is not essential.

Other catalysts suitable for the fluorinations of step (a) are compositions comprising a zinc halide and  $\alpha$ -chromium oxide and compositions obtained by treatment of said compositions comprising a zinc halide and  $\alpha$ -chromium oxide with a fluorinating agent. U. S. Patent  
5 No. 3,878,257 discloses an example of such catalysts. The amount of zinc relative to the total of chromium and zinc in these compositions is preferably from about 0.1 atom % to about 25 atom %; and is more preferably from about 2 atom % to about 10 atom %. Of note are compositions wherein a zinc halide is supported on a support comprising  
10  $\alpha$ -chromium oxide. Preferably, the  $\alpha$ -chromium oxide is prepared according to U. S. Patent No. 5,036,036. Pretreatment with a fluorinating agent can be carried out as indicated above for the calcined zinc chromite/ $\alpha$ -chromium oxide compositions.

Compounds that are produced in the fluorination process in step (a)  
15 include the  $\text{CF}_3\text{CCl}=\text{CF}_2$  (CFC-1215xc) and  $\text{CF}_3\text{CHClCF}_3$  (HCFC-226da).

Halopropane by-products having a higher degree of fluorination than HCFC-226da that may be formed in step (a) include  $\text{CF}_3\text{CClCF}_3$  (CFC-217ba).

Halopropane by-products having a lower degree of fluorination than  
20 HCFC-226da that may be formed in step (a) include  $\text{CF}_3\text{CHClCClF}_2$  (HCFC-225da). Other halopropane by-products which may be formed include CFC-216aa ( $\text{CF}_3\text{CCl}_2\text{CF}_3$ ).

Halopropene by-products having a lower degree of fluorination than CFC-1215xc that may be formed in step (a) include *E*- and *Z*-  
25  $\text{CF}_3\text{CCl}=\text{CClF}$  (CFC-1214xb) and  $\text{CF}_3\text{CCl}=\text{CCl}_2$  (CFC-1213xa).

Typically, the effluent from step (a) comprising CFC-1215xc and HCFC-226da, and optionally HF, is separated from lower boiling components, mainly comprising HCl along with some over-fluorinated products such as CFC-217ba and azeotropic HF, and from the higher  
30 boiling components comprising the under-fluorinated components such as HCFC-225da,  $\text{C}_3\text{Cl}_4\text{F}_4$  isomers, and CFC-1213xa.

In one embodiment of the process of this invention, the reactor effluent from step (a) may be delivered to a distillation column in which HCl and any HCl azeotropes are removed from the top of column while the  
35 higher boiling components are removed at the bottom of the column. The products recovered at the bottom of the first distillation column are then delivered to a second distillation column in which CFC-217ba, and some HF, are separated at the top of the column and the remaining HF and



organic products, comprising  $\text{CF}_3\text{CHClCF}_3$ ,  $\text{CF}_3\text{CCl}=\text{CF}_2$ , and higher boiling components, are removed from the bottom of the column. The products recovered from the bottom of the second distillation column are then delivered to a third distillation column in which  $\text{CF}_3\text{CHClCF}_3$ ,  
5  $\text{CF}_3\text{CCl}=\text{CF}_2$ , and HF, are separated at the top of the column, and any remaining HF and under-fluorinated components are removed from the bottom of the column.

The mixture of  $\text{CF}_3\text{CHClCF}_3$ ,  $\text{CF}_3\text{CCl}=\text{CF}_2$ , and HF, from the top of the third distillation column may be delivered to step (b) or may optionally  
10 be delivered to a decanter maintained at a suitable temperature to cause separation of an organic-rich liquid phase and an HF-rich liquid phase. The HF-rich phase may be distilled to recover HF which is then recycled to step (a). The organic-rich phase may then be delivered to step (b) or may be distilled to give pure HCFC-226da and CFC-1215xc.

15 In one embodiment of the process of this invention said under-fluorinated components such as HCFC-225da,  $\text{C}_3\text{Cl}_2\text{F}_4$ , and  $\text{CF}_3\text{CCl}=\text{CCl}_2$  (CFC-1213xa) may be returned to step (a).

In step (b) of the process, the  $\text{CF}_3\text{CHClCF}_3$  and  $\text{CF}_3\text{CCl}=\text{CF}_2$  produced in step (a) are reacted with hydrogen ( $\text{H}_2$ ), optionally in the  
20 presence of HF.

In one embodiment of step (b), a mixture comprising  $\text{CF}_3\text{CHClCF}_3$  and  $\text{CF}_3\text{CCl}=\text{CF}_2$ , and optionally HF, is delivered in the vapor phase, along with hydrogen ( $\text{H}_2$ ), to a reactor fabricated from nickel, iron, titanium, or their alloys, as described in U. S. Patent No. 6,540,933; the teachings of  
25 this disclosure are incorporated herein by reference. A reaction vessel of these materials (e.g., a metal tube) optionally packed with the metal in suitable form may also be used. When reference is made to alloys, it is meant a nickel alloy containing from 1 to 99.9% (by weight) nickel, an iron alloy containing 0.2 to 99.8% (by weight) iron, and a titanium alloy  
30 containing 72-99.8% (by weight) titanium. Of note is use of an empty (unpacked) reaction vessel made of nickel or alloys of nickel such as those containing 40% to 80% nickel, e.g., Inconel™ 600 nickel alloy, Hastelloy™ C617 nickel alloy, or Hastelloy™ C276 nickel alloy.

When used for packing, the metal or metal alloys may be particles  
35 or formed shapes such as perforated plates, rings, wire, screen, chips, pipe, shot, gauze, or wool.

The temperature of the reaction in this embodiment can be between about 350°C and about 600°C, and is preferably at least about 450°C.

The molar ratio of hydrogen to the CFC-1215xc/HCFC-226da mixture fed to the reaction zone should be in the range of about 0.1 mole H<sub>2</sub> per mole of CFC-1215xc/HCFC-226da mixture to about 60 moles of H<sub>2</sub> per mole of CFC-1215xc/HCFC-226da mixture, more preferably from about 0.4 to 10 moles of H<sub>2</sub> per mole of CFC-1215xc/HCFC-226da mixture.

In another embodiment of the process, the contacting of hydrogen with the CFC-1215xc/HCFC-226da mixture produced in step (a), and optionally HF, is carried out in the presence of a hydrogenation catalyst. Hydrogenation catalysts suitable for use in this embodiment include catalysts comprising at least one metal selected from the group consisting of rhenium, iron, ruthenium, osmium, cobalt, rhodium, iridium, nickel, palladium, and platinum. Said catalytic metal component is typically supported on a carrier such as carbon or graphite or a metal oxide, fluorinated metal oxide, or metal fluoride where the carrier metal is selected from the group consisting of magnesium, aluminum, titanium, vanadium, chromium, iron, and lanthanum.

Of note are carbon supported catalysts in which the carbon support has been washed with acid and has an ash content below about 0.1% by weight. Hydrogenation catalysts supported on low ash carbon are described in U.S. Patent No. 5,136,113, the teachings of which are incorporated herein by reference. Also of note are catalysts comprising at least one metal selected from the group consisting of palladium, platinum, and rhodium supported on alumina (Al<sub>2</sub>O<sub>3</sub>), fluorinated alumina, or aluminum fluoride (AlF<sub>3</sub>).

The supported metal catalysts may be prepared by conventional methods known in the art such as by impregnation of the carrier with a soluble salt of the catalytic metal (e.g., palladium chloride or rhodium nitrate) as described by Satterfield on page 95 of *Heterogenous Catalysis in Industrial Practice*, 2<sup>nd</sup> edition (McGraw-Hill, New York, 1991). The concentration of the catalytic metal(s) on the support is typically in the range of about 0.1% by weight of the catalyst to about 5% by weight.

The relative amount of hydrogen contacted with CFC-1215xc and HCFC-226da when a hydrogenation catalyst is used is typically from about the stoichiometric ratio of hydrogen to CF<sub>3</sub>CHClCF<sub>3</sub>/CF<sub>3</sub>CCl=CF<sub>2</sub> mixture to about 10 moles of H<sub>2</sub> per mole of CF<sub>3</sub>CHClCF<sub>3</sub>/CF<sub>3</sub>CCl=CF<sub>2</sub> mixture. The stoichiometric ratio of hydrogen to the CF<sub>3</sub>CHClCF<sub>3</sub>/CF<sub>3</sub>CCl=CF<sub>2</sub> mixture depends on the relative amounts of the two components in the

mixture. The stoichiometric amounts of  $H_2$  required to convert HCFC-226da and CFC-1215xc to  $CF_3CH_2CF_3$  and  $CF_3CH_2CHF_2$ , are one and two moles, respectively.

5        Suitable temperatures for the catalytic hydrogenation are typically from about 100°C to about 350°C, preferably from about 125°C to about 300°C. Temperatures above about 350°C tend to result in defluorination side reactions; temperatures below about 125°C will result in incomplete substitution of Cl for H in the starting materials. The reactions are typically conducted at atmospheric pressure or superatmospheric pressure.

10        The products from the step (b) reaction zone(s) typically include HCl,  $CF_3CH_2CF_3$  (HFC-236fa),  $CF_3CH_2CHF_2$  (HFC-245fa), and small amounts of lower boiling by-products (typically including propane,  $CF_3CH=CF_2$  (HFC-1225zc), *E*- and *Z*- $CF_3CH=CHF$  (HFC-1234ze), and/or  $CF_3CH_2CH_3$  (HFC-263fb)) and higher boiling by-products and  
15 intermediates (typically including  $CF_3CHFCH_3$  (HFC-254eb) and/or  $CF_3CHClCHF_2$  (HCFC-235da)) as well as any unconverted starting materials and any HF carried over from step (a).

20        In step (c), the desired products are recovered. Products from step (b) may be delivered to a separation unit to recover  $CF_3CH_2CF_3$  and  $CF_3CH_2CHF_2$  individually, as a mixture, or as their HF azeotropes.

Partially chlorinated components such as HCFC-235da may be recovered and recycled back to step (b).

25        The reactor, distillation columns, and their associated feed lines, effluent lines, and associated units used in applying the processes of this invention should be constructed of materials resistant to hydrogen fluoride and hydrogen chloride. Typical materials of construction, well-known to the fluorination art, include stainless steels, in particular of the austenitic type, the well-known high nickel alloys, such as Monel™ nickel-copper alloys, Hastelloy™ nickel-based alloys and, Inconel™ nickel-chromium  
30 alloys, and copper-clad steel.

The following specific embodiments are to be construed as merely illustrative, and do not constrain the remainder of the disclosure in any way whatsoever.

EXAMPLESLEGEND

- |   |   |  |
|---|---|--|
|   | 215aa is $\text{CF}_3\text{CCl}_2\text{CClF}_2$ | 216aa is $\text{CF}_3\text{CCl}_2\text{CF}_3$  |
| 5 | 217ba is $\text{CF}_3\text{CClFCF}_3$           | 225da is $\text{CF}_3\text{CHClCClF}_2$        |
|   | 226da is $\text{CF}_3\text{CHClCF}_3$           | 1213xa is $\text{CF}_3\text{CCl}=\text{CCl}_2$ |
|   | 1214 is $\text{C}_3\text{Cl}_2\text{F}_4$       | 1215xc is $\text{CF}_3\text{CCl}=\text{CF}_2$  |

Catalyst PreparationCOMPARATIVE PREPARATION EXAMPLE 1

- 10                      Preparation of 100% Chromium Catalyst (400°C)

A solution of 400 g  $\text{Cr}(\text{NO}_3)_3[9(\text{H}_2\text{O})]$  (1.0 mole) in 1000 mL of deionized water was treated dropwise with 477 mL of 7.4M aqueous ammonia raising the pH to about 8.5. The slurry was stirred at room temperature overnight. After re-adjusting the pH to 8.5 with ammonia, the mixture was poured into evaporating dishes and dried in air at 120°C. The dried solid was then calcined in air at 400°C; the resulting solid weighed 61.15 g. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 28.2 g (20 mL) was used in Comparative Example 1.

COMPARATIVE PREPARATION EXAMPLE 2

- 20                      Preparation of 2% Zinc on Alumina Catalyst

Aluminum oxide (4.90 moles, Harshaw 3945, dried at 110°C) was added to a solution of 20.85 g  $\text{ZnCl}_2$  (0.153 mole) dissolved in 460 mL of distilled water. Water was evaporated from the mixture with stirring and then dried at 110°C for three days. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 21.1 g (30 mL) was used in Comparative Example 3.

PREPARATION EXAMPLE 1

Preparation of 2% Zinc chloride supported on Chromium oxide

- A solution of 1.20 g  $\text{ZnCl}_2$  (8.81 moles) in 60 mL of deionized water contained in a 125 mm X 65 mm glass dish was treated with 60.00 g (0.357 mole) of 12-20 mesh  $\text{Cr}_2\text{O}_3$ . The dish was placed on a warm hot plate and the slurry allowed to dry with occasional stirring. The resulting solid was then dried overnight at 130°C; the resulting solid weighed 60.42 g. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 41.5 g (30 mL) was used in Example 1.

### PREPARATION EXAMPLE 2

#### Preparation of 95% Chromium/5% Zinc Catalyst (450°C)

A solution of 380.14 g  $\text{Cr}(\text{NO}_3)_3[9(\text{H}_2\text{O})]$  (0.950 mole) and 14.87 g  $\text{Zn}(\text{NO}_3)_2[6(\text{H}_2\text{O})]$  (0.050 mole) was prepared in 1000 mL of deionized water. The solution was treated with 450 mL of 7.4M aqueous ammonium hydroxide over the course of one hour; the pH increased from 1.7 to pH 8.4. The slurry was stirred at room temperature overnight and then dried at 120°C in an oven in the presence of air. The dried solid was then calcined in air at 450°C for 20 hours; the resulting solid weighed 76.72 g. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 38.5 g (25 mL) was used in Example 6.

### PREPARATION EXAMPLE 3

#### Preparation of 90% Chromium/10% Zinc Catalyst (900°C)

A solution of 360.13 g  $\text{Cr}(\text{NO}_3)_3[9(\text{H}_2\text{O})]$  (0.900 mole) and 29.75 g  $\text{Zn}(\text{NO}_3)_2[6(\text{H}_2\text{O})]$  (0.100 mole) was prepared in 1000 mL of deionized water. The solution was treated with 450 mL of 7.4M aqueous ammonium hydroxide over the course of 1.4 hours; the pH increased from 1.9 to pH 8.4. The slurry was stirred at room temperature overnight and then dried at 120°C in the presence of air. The dried solid was then calcined in air at 900°C for 20 hours; the resulting solid weighed 75.42 g. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 42.3 g (25 mL) was used in Example 8.

### PREPARATION EXAMPLE 4

#### Preparation of 95% Chromium/5% Zinc Catalyst (900°C)

A solution of 380.14 g  $\text{Cr}(\text{NO}_3)_3[9(\text{H}_2\text{O})]$  (0.950 mole) and 14.87 g  $\text{Zn}(\text{NO}_3)_2[6(\text{H}_2\text{O})]$  (0.050 mole) was prepared in 1000 mL of deionized water. The solution was treated with 450 mL of 7.4M aqueous ammonium hydroxide over the course of one hour; the pH increased from 1.7 to pH 8.4. The slurry was stirred at room temperature overnight and then dried at 120°C in an oven in the presence of air. The dried solid was then calcined in air at 900°C for 20 hours; the resulting solid weighed 70.06 g. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 25.3 g (14 mL) was used in Example 7.

### PREPARATION EXAMPLE 5

#### Preparation of 98% Chromium/2% Zinc Catalyst (900°C)

A solution of 392.15 g  $\text{Cr}(\text{NO}_3)_3[9(\text{H}_2\text{O})]$  (0.980 mole) and 5.94 g  $\text{Zn}(\text{NO}_3)_2[6(\text{H}_2\text{O})]$  (0.020 mole) was prepared in 1000 mL of deionized water. The solution was treated with 450 mL of 7.4M aqueous ammonium

- hydroxide over the course of 0.58 hour; the pH increased from 1.67 to pH 8.35. The slurry was stirred at room temperature overnight and then dried at 120°C in an oven in the presence of air. The dried solid was then calcined in air at 900°C for 21 hours; the resulting solid weighed 66.00 g.
- 5 The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 44.9 g (23 mL) was used in Example 5.

#### PREPARATION EXAMPLE 6

- Preparation of 10% Zinc chloride supported on Chromium oxide
- A solution of 6.0 g  $\text{ZnCl}_2$  (44 moles) in 300 mL of deionized water
- 10 contained in a 170 mm X 90 mm glass dish was treated with 60.00 g (0.357 mole) of 12-20 mesh  $\text{Cr}_2\text{O}_3$ . The dish was placed on a warm hot plate and the slurry allowed to dry with occasional stirring. The resulting solid was then dried overnight at 130°C; the resulting solid weighed 65.02 g. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and
- 15 37.5 g (25 mL) was used in Example 2.

#### PREPARATION EXAMPLE 7

- Preparation of 98.1% Chromium/1.9% Zinc Catalyst (550°C)
- A solution of 516.46 g  $\text{Cr}(\text{NO}_3)_3[9(\text{H}_2\text{O})]$  (1.29 moles) and 7.31 g  $\text{Zn}(\text{NO}_3)_2[6(\text{H}_2\text{O})]$  (0.0246 mole) was prepared in 500 mL of distilled water
- 20 in 1L beaker resting on a hot plate. The mixture was then transferred to a Pyrex™ container and the container placed in a furnace. The container was heated from room temperature to 125°C at 10°C/min and then held at 125°C for six hours. The container was heated from 125°C to 350°C at 1°C/min and then held at 350°C for six hours. The container was heated
- 25 from 350°C to 550°C at 1°C/min and then held at 550°C for 24 hours. The catalyst was pelletized (-12 to +20 mesh, (1.68 to 0.84 mm)) and 29.9 g (20 mL) was used in Examples 3 and 4.

#### EXAMPLES 1-8 and COMPARATIVE EXAMPLES 1-3

##### General Procedure for Fluorination

- 30 A weighed quantity of pelletized catalyst was placed in a 5/8" (1.58 cm) diameter Inconel™ nickel alloy reactor tube heated in a fluidized sand bath. The tube was heated from 50°C to 175°C in a flow of nitrogen (50 cc/min;  $8.3(10)^{-7}\text{m}^3/\text{sec}$ ) over the course of about one hour. HF was then admitted to the reactor at a flow rate of 50 cc/min ( $8.3(10)^{-7}\text{m}^3/\text{sec}$ ).
- 35 After 0.5 to 2 hours the nitrogen flow was decreased to 20 cc/min ( $3.3(10)^{-7}\text{m}^3/\text{sec}$ ) and the HF flow increased to 80 cc/min ( $1.3(10)^{-6}\text{m}^3/\text{sec}$ ); this flow was maintained for about 1 hour. The reactor temperature was then gradually increased to 400°C over 3 to 5 hours. At

the end of this period, the HF flow was stopped and the reactor cooled to 300°C under 20 sccm ( $3.3(10)^{-7}\text{m}^3/\text{sec}$ ) nitrogen flow. CFC-1213xa was fed from a pump to a vaporizer maintained at about 118°C. The CFC-1213xa vapor was combined with the appropriate molar ratios of HF in a 0.5 inch (1.27 cm) diameter Monel™ nickel alloy tube packed with Monel™ turnings. The mixture of reactants then entered the reactor; the contact time was 15 seconds unless otherwise indicated. All reactions were conducted at a nominal pressure of one atmosphere. The results of CFC-1213xa fluorination over the several catalysts are shown in Table 1; analytical data is given in units of GC area %.

Exa. HF/1213 Temp			Catalyst	Products, GC Area %						
No.	Ratio	°C		1215xc	217ba	226da	216aa	225da	1214's	1213xa
1 <sup>a</sup>	20/1	260	2% ZnCl <sub>2</sub> /Cr <sub>2</sub> O <sub>3</sub>	65.9	-	19.9	0.9	1.60	3.3	4.8
2 <sup>a</sup>	6/1	280	10% ZnCl <sub>2</sub> /Cr <sub>2</sub> O <sub>3</sub>	42.4	-	1.2	0.04	2.8	15.4	37.7
3 <sup>b</sup>	20/1	300	Cr/Zn 98.1/1.9 550°C	20.1	0.3	64.2	9.1	1.6	1.6	0.8
4	20/1	350	Cr/Zn 98.1/1.9 550°C	7.9	0.4	77.2	11.2	0.2	0.7	0.4
5	6/1	280	Cr/Zn 98/2 900°C	34.8	-	1.1	0.04	2.5	16.4	44.6
6 <sup>b</sup>	6/1	280	Cr/Zn 95/5 450°C	1.3	0.01	73.0	6.5	0.4	1.3	1.5
7	30/1	320	Cr/Zn 95/5 900°C	79.0	-	5.9	0.3	-	4.0	8.7
8	20/1	280	Cr/Zn 90/10 900°C	70.3	-	10.2	1.0	3.1	8.1	6.6
C1 <sup>c</sup>	20/1	300	100% Cr <sub>2</sub> O <sub>3</sub>	0.3	0.9	89.7	7.8	-	8.1	6.6
C2 <sup>a,c,d</sup>	20/1	300	100% Cr <sub>2</sub> O <sub>3</sub> (HSA)	0.2	-	94.5	3.9	-	-	-
C3 <sup>a,c</sup>	6/1	280	2% Zn/Al <sub>2</sub> O <sub>3</sub>	2.5	0.02	90.5	0.02	1.4	1.4	3.2

- a. The contact time was 30 seconds.  
b. Product contained 12.8 GC area % CFC-215aa.  
c. Comparative Example.  
d. High surface area chromium oxide from a commercial source; the catalyst was activated with HF prior to use following the general procedure.



### CLAIMS

What is claimed is:

1. A process for the manufacture of 1,1,1,3,3-pentafluoropropane and 1,1,1,3,3,3-hexafluoropropane, comprising:

- 5 (a) reacting HF and at least one halopropene of the formula  $CX_3CCl=CCIX$ , wherein each X is independently selected from the group consisting of F and Cl, to produce a product comprising  $CF_3CCl=CF_2$  and  $CF_3CHClCF_3$ , wherein said  $CF_3CCl=CF_2$  and  $CF_3CHClCF_3$  are produced in the presence of a fluorination catalyst comprising at least one composition selected from the group consisting of (i) compositions comprising  $ZnCr_2O_4$  and crystalline  $\alpha$ -chromium oxide, (ii) compositions comprising a zinc halide and  $\alpha$ -chromium oxide and (iii) compositions of (i) or (ii) which have been treated with a fluorinating agent;
- 10 (b) reacting  $CF_3CCl=CF_2$  and  $CF_3CHClCF_3$  produced in (a) with hydrogen to produce a product comprising  $CF_3CH_2CHF_2$  and  $CF_3CH_2CF_3$ ; and
- 15 (c) recovering  $CF_3CH_2CHF_2$  and  $CF_3CH_2CF_3$  from the product produced in (b).
- 20

2. The process of Claim 1 wherein in (a) the catalyst is selected from the group consisting of (i) compositions comprising  $ZnCr_2O_4$  and crystalline  $\alpha$ -chromium oxide and (iii) compositions of (i) which have been treated with a fluorinating agent.

25

3. The process of Claim 2 wherein the amount of zinc relative to the total of chromium and zinc in the catalyst composition is from about 1 atom % to about 25 atom %.

4. The process of Claim 2 wherein the catalyst is selected from the group consisting of (i) compositions comprising  $ZnCr_2O_4$  and crystalline  $\alpha$ -chromium oxide wherein the  $ZnCr_2O_4$  contains between about 10 atom percent and 67 atom percent of the chromium in the composition and at least about 70 atom percent of the zinc in the composition, and wherein at least about 90 atom percent of the chromium present as chromium oxide in the composition is present as  $ZnCr_2O_4$  or crystalline  $\alpha$ -chromium oxide and (iii) compositions of (i) which have been treated with a fluorinating agent.

30

35

5. The process of Claim 1 wherein in (a) the catalyst is selected from the group consisting of (ii) compositions comprising a zinc halide and  $\alpha$ -chromium oxide and (iii) compositions of (ii) which have been treated with a fluorinating agent.

5        6. The process of Claim 5 wherein the amount of zinc relative to the total of chromium and zinc in the catalyst composition is from about 0.1 atom % to about 25 atom %.

10       7. The process of Claim 5 wherein the catalyst is selected from the group consisting of (ii) compositions wherein a zinc halide is supported on a support comprising  $\alpha$ -chromium oxide and (iii) compositions of (ii) which have been treated with a fluorinating agent; and wherein the amount of zinc relative to the total of chromium and zinc in the catalyst composition is from about 2 atom % to about 10 atom %.

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US2004/034455

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C07C19/08 C07C17/20 C07C17/21 C07C17/23

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C07C B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, BEILSTEIN Data, CHEM ABS Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 763 706 A (TUNG ET AL) 9 June 1998 (1998-06-09) claims 1,24	1
A	EP 0 611 744 A (BAYER AG) 24 August 1994 (1994-08-24) the whole document	1
A	EP 0 442 075 A (BAYER AG) 21 August 1991 (1991-08-21) page 2, line 45 - line 46 page 3, line 13 - line 25 page 4; tables	1
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

25 February 2005

Date of mailing of the international search report

09/03/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Kardinal, S

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US2004/034455

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 98/10862 A (IMPERIAL CHEMICAL INDUSTRIES PLC; SCOTT, JOHN, DAVID; WATSON, MICHAEL,) 19 March 1998 (1998-03-19) page 1, line 9 - line 13 page 2, line 4 - page 4, line 6 page 7, line 25 - line 30 examples	1
A	EP 0 657 408 A (ELF ATOCHEM S.A) 14 June 1995 (1995-06-14) page 2, line 1 - line 3 page 6-8, catalyst 11	1
A	EP 0 502 605 A (IMPERIAL CHEMICAL INDUSTRIES PLC) 9 September 1992 (1992-09-09) the whole document	1

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

International Application No  
PCT/US2004/034455

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 5763706	A	09-06-1998	WO	9800378 A1	08-01-1998
EP 0611744	A	24-08-1994	DE	4305164 A1	25-08-1994
			BR	9400604 A	23-08-1994
			DE	59401009 D1	19-12-1996
			EP	0611744 A1	24-08-1994
			ES	2093458 T3	16-12-1996
			JP	6256235 A	13-09-1994
			MX	9401224 A1	31-08-1994
EP 0442075	A	21-08-1991	DE	4004495 A1	22-08-1991
			CA	2036220 A1	15-08-1991
			DE	59002322 D1	16-09-1993
			EP	0442075 A1	21-08-1991
			ES	2044382 T3	01-01-1994
			JP	2672191 B2	05-11-1997
			JP	4211027 A	03-08-1992
			US	5171901 A	15-12-1992
WO 9810862	A	19-03-1998	CA	2263711 A1	19-03-1998
			EP	0925112 A1	30-06-1999
			WO	9810862 A1	19-03-1998
			JP	2001500059 T	09-01-2001
			US	2001011061 A1	02-08-2001
EP 0657408	A	14-06-1995	FR	2713633 A1	16-06-1995
			AU	8034094 A	15-06-1995
			CA	2136938 A1	10-06-1995
			CN	1107827 A	06-09-1995
			DE	69406525 D1	04-12-1997
			DE	69406525 T2	07-05-1998
			EP	0657408 A1	14-06-1995
			ES	2110201 T3	01-02-1998
			GR	3025863 T3	30-04-1998
			JP	7206728 A	08-08-1995
EP 0502605	A	09-09-1992	AT	140399 T	15-08-1996
			AU	658161 B2	06-04-1995
			AU	1032492 A	10-09-1992
			BR	9200361 A	10-11-1992
			CA	2059983 A1	08-09-1992
			CN	1064628 A	23-09-1992
			CN	1130615 A ,C	11-09-1996
			CS	9200171 A3	16-09-1992
			DE	69212183 D1	22-08-1996
			DE	69212183 T2	05-12-1996
			DK	502605 T3	28-10-1996
			EP	1350564 A1	08-10-2003
			EP	0502605 A1	09-09-1992
			EP	0666105 A2	09-08-1995
			ES	2089381 T3	01-10-1996
			FI	920273 A	08-09-1992
			GR	3020970 T3	31-12-1996
			HU	63825 A2	28-10-1993
			IE	920163 A1	09-09-1992
			IN	185352 A1	06-01-2001
			JP	5220400 A	31-08-1993
			KR	217353 B1	01-09-1999

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCI/US2004/034455

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0502605	A	MX 9200998 A1	01-09-1992
		NO 920299 A	08-09-1992
		PL 293283 A1	05-10-1992
		SG 50565 A1	20-07-1998
		RU 2032464 C1	10-04-1995
		US 5449656 A	12-09-1995
		US 5623092 A	22-04-1997
		US 5281568 A	25-01-1994
		ZA 9200396 A	25-11-1992

CL2372

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record.**

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**